Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-08-28-06** **Date: 31-08-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP,
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer's Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	28-08-18
Sample ID No	:	2018-08-28-06 /01
Sample Type	:	ACC 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	29-08-18
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	2.95	–
2	Finess by Air permeablity method (m^2/kg,Min)	289.7	225m^2/kg, Min
3	Density (gm/cc)	3.11	–
4	Standard Consistency (%)	29.5%	Not specified
5	Initial Setting time	175 minutes	Not less than 30 minutes
6	Final Setting time	285 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.0mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

Page 1/1

****End of Report****

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-08-28-06** **Date: 26-09-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer's Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	28-08-18
Sample ID No	:	2018-08-28-06 /01
Sample Type	:	ACC 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	29-08-18
Environmental Conditions during test	:	Temperature: 26˚C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	29.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.5N/mm^2	Not less than 37 N/mm^2
3	28 Days	57.5N/mm^2	Not less than 53 N/mm^2

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-08-28-06** **Date: 31-08-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer's Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	28-08-18
Sample ID No	:	2018-08-28-06 /02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	28-08-18

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	211	211	1.4	98.6	90-100
3	20 mm	7868	8079	53.9	46.1	30-70
4	10 mm	4455	12534	83.6	16.4	10-35
5	4.75 mm	2011	14545	97.0	3.0	0-5
6	Pan	455	15000	100.0	0	---

CIVIL Pro Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2018-08-28-06** **Date: 31-08-18**

Sample ID No : 2018-08-28-06 /02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	**11.5**	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	**11.9**	
3	Specific Gravity	**2.63**	_
4	Bulk Density(Loose) (Kg/l)	**1.39**	_
5	Bulk Density(Compacted) (Kg/l)	**1.45**	_
6	Water Absorption(%)	**0.21**	_

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-08-28-06** **Date: 30-08-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	28-08-18
Sample ID No	:	2018-08-28-06 /02(b)
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	28-08-18

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	385	385	7.7	92.3	90-100
3	10 mm	2859	3244	64.9	35.1	25-55
4	4.75 mm	1477	4721	94.4	5.6	0-10
5	Pan	279	5000	100	0	–

CIVIL PRO Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2018-08-28-06** **Date: 30-08-18**

Sample ID No : 2018-08-28-06 /02(b)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	10.1	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.5	
3	Specific Gravity	2.64	–
4	Bulk Density(Loose) (Kg/l)	1.41	–
5	Bulk Density(Compacted) (Kg/l)	1.47	–
6	Water Absorption(%)	0.38	–
7	Aggregate crushing Value(%)	23.8	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	24.5	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2018-08-28-06** **Date: 30-08-18**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.

Agency : Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24

Customer's Reference : EE/BTP/BBMP/E-PMT/220/2014-15

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 28-08-18

Sample ID No : 2018-08-28-06 /03

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 28-08-18

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	22	22	2.2	97.8	90-100	90-100	90-100	95-100
3	2.36 mm	202	224	22.4	77.6	60-95	75-100	85-100	95-100
4	1.18 mm	198	422	42.2	57.8	30-70	55-90	75-100	90-100
5	600 micron	178	600	60.0	40.0	15-34	35-59	60-79	80-100
6	300 micron	243	843	84.3	15.7	5-20	8-30	12-40	15-50
7	150 micron	101	944	94.4	5.6	0-10	0-10	0-10	0-15
8	Pan	56	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ., ಬೆಂಗಳೂರು-24

CIVIL PRO Sig..... Date..... BANGALORE

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2018-08-28-06** **Date: 30-08-18**

Sample ID No : 2018-08-28-06 /03

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.24	–
2	Specific Gravity	2.54	–
3	Material finer than 75 micron(%)	5.1	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST RESULTS OF STEEL

Lab ID	:	**CP-2018-08-28-06** **Date: 30-08-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer's Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	28-08-18
Sample ID No	:	2018-08-28-06 /04
Sample Type	:	Sunvik
Reference to BIS codes	:	IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012.
Date of test:	:	29-08-18

Sl.No	Identification of sample	Grade of the sample	Diameter of the steel bar	Weight of the sample	Yield stress	Tensile strength	Elongation	Bend test	Rebend test
			(mm)	(kg/m)	(N/mm2)	(N/mm2)	(%)		
1	Sunvik	Fe500	8	0.392	544	652	21.0%	Satisfactory	Satisfactory
2	Sunvik	Fe500	10	0.612	558	671	20.0%	Satisfactory	Satisfactory
3	Sunvik	Fe500	12	0.883	568	680	20.0%	Satisfactory	Satisfactory

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

End of Report

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-09-05-04** **Date: 10/09/2018**

Customer : Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.

Address : Byatarayanapura Sub Division, BBMP, Bangalore.

Project Name : Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.

Agency : Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24

Customer's Reference : EE/BTP/BBMP/E-PMT/220/2014-15

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-09-18

Sample ID No : 2018-09-05-04 /01

Customer ID : Drain Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M20 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/09/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Concrete	M20	03/09/2018	10/09/2018	149.88 X 151.24 X 150.63	22668	8.174	417.1	18.4	18.2
2	Drain Concrete	M20	03/09/2018	10/09/2018	150.47 X 150.66 X 148.79	22670	8.166	405.8	17.9	
3	Drain Concrete	M20	03/09/2018	10/09/2018	151.66 X 149.65 X 151.55	22696	8.152	413.1	18.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

)	:	**CP-2018-09-05-04** **Date: 01/10/2018**
omer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
dress	:	Byatarayanapura Sub Division, BBMP, Bangalore.
roject Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer's Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-09-18
Sample ID No	:	2018-09-05-04 /02
Customer ID	:	Drain Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M20 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	01/10/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Concrete	M20	03/09/2018	01/10/2018	149.88 X 151.24 X 150.47	22668	8.174	539.5	23.8	23.1
2	Drain Concrete	M20	03/09/2018	01/10/2018	150.65 X 150.26 X 149.78	22637	8.166	532.0	23.5	
3	Drain Concrete	M20	03/09/2018	01/10/2018	151.66 X 149.62 X 151.56	22691	8.149	501.5	22.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST RESULTS OF GRADATION FOR WMM

Lab ID	:	**CP-RW-2018-09-06-02** **Date: 08-09-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-09-18
Sample ID No	:	2018-09-06-02/01
Type of Mix	:	WMM (Wet Mix Macadam)
Date of test	:	06-09-18
Oven Dry Weight	:	11000 Grams

IS Sieve Size(mm)	Weight Retained (gm)	Cumulative Weight Retained (gm)	% Cumulative Weight Retained	% Passing	Spec.I.Vide Table 400.13 MORTH Specification
53	0	0	0.0	100.0	100
45	214	214	1.9	98.1	95-100
22.4	2201	2415	22.0	78.0	60-80
11.2	2377	4792	43.6	56.4	40-60
4.75	2745	7537	68.5	31.5	25-40
2.36	1678	9215	83.8	16.2	15-30
0.6	498	9713	88.3	11.7	8-22
0.075	1081	10794	98.1	1.9	0-5

Note:-

The results pertain to the samples received and tested.
All information Furnished by Customer/ Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬ್ಯಾಟರಾಯನಪುರ ಉಪ ವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬೆಂಗಳೂರು-24

Page 1/1
End of Report

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

TEST RESULTS OF GRADATION FOR SDBC
IS 2386 (Part 1) 1963 (RA 2007)

Lab ID	:	**CP-RW-2018-09-17-02** **Date: 19-09-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-09-18
Sample ID No	:	2018-09-17-02/01
Type of Mix	:	SDBC-Plant (Semi Dense Bituminous Concrete)
Date of test	:	17-09-18
Weight of Sample	:	5000 Grams

IS Sieve Size (mm)	Weight Retained (gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Secified limits as per MORTH specification table 500-15(grading-2)
13.2	0	0	0.0	100.0	100
9.5	312	312	6.2	93.8	90-100
4.75	2477	2789	55.8	44.2	35-51
2.36	775	3564	71.3	28.7	24-39
1.18	518	4082	81.6	18.4	15-30
0.3	378	4460	89.2	10.8	9-19
0.075	152	4612	92.2	7.8	3-8
PAN	388	5000	100.0	0.0	0

Note:-
The results pertain to the samples received and tested.
All information Furnished by Customer/ Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

Page 1/1
End of Report

TEST REPORT OF AGGEGRATE STRIPPING VALUE OF ROAD AGGRGATE (IS:6241)

Lab ID	:	**CP-RW-2018-09-17-02** **Date: 20-09-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-09-18
Sample ID No	:	2018-09-17-02/01
Type of Mix	:	SDBC (Semi Dense Bituminous Concrete)
Date of test	:	17-09-18

Type of Binder	:	60/70
% of Binder Used	:	5.0%
Weight of Aggregate	:	200.0 gm
Weight of Binder	:	10.0 gm
Temperature of water bath	:	40°C

No of test	Retained Stripping Percentage	Stripping Percentage	Average Retained Stripping Percentage	Secified limits as per MORTH specification table 500-8
1	97.5	2.5	97.7	Minimum Retained Coating 95%
2	98.5	1.5		
3	97.0	3.0		

Note:-
The results pertain to the samples received and tested.
All information Furnished by Customer/ Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TESTS RESULTS ON STABILITY OF MIX

Lab ID	:	**CP-RW-2018-09-17-02** **Date: 20-09-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Hot Mix Plant, Bangalore
Sample Condition	:	Satisfactory
Date of Receipt	:	17-09-18
Sample ID No	:	2018-09-17-02/01
Type of Mix	:	SDBC (Semi Dense Bituminous Concrete)
Date of test	:	17-09-18

The results of the tests conducted on the Semi Dense Bituminous Concrete mix sample are as follow

Sl.No	Particulars of observations	TEST 1	TEST 2	Secified limits as per MORTH specification table 500-16
1	Marshal Stability at 60°C, KN	11.1	10.9	8.2KN(min)
2	Marshal flow at 60°C, mm	3.48	3.32	2-4
3	Percent air Voids	4.48	4.52	3-5
4	Percent Voids in mineral Aggregate(VMA %)	13.75	13.88	13-15
5	Percent Voids filled with Bitumen(VFB %)	71.98	71.6	65-75
6	Density, g/cc	2.64	2.65	–

Note:-
The results pertain to the samples received and tested.
All information Furnished by Customer/ Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO Sig..... Date..... BANGALORE

Page 1/1
End of Report

TEST RESULTS OF BITUMEN BINDAR CONTENT AND GRADATION FOR SDBC
(IS 2386:(Part 1) 1963 (RA2011)

Lab ID	:	**CP-RW-2018-09-21-02** **Date: 22-09-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-09-18
Sample ID No	:	2018-09-21-02/01
Type of Mix	:	SDBC (Semi Dense Bituminous Concrete)
Date of test	:	21-09-18

Sl.no	Description	Index	Trail 1	Trail 2
1	Weight of the Sample	A	500	500
2	Weight of the sample After extraction	B	476	477
3	Bitumen percentage	$\frac{A-B}{A} \times 100$	4.80	4.60
4	Average percentage	%	4.7	

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Lab ID : **CP-RW-2018-09-21-02** **Date: 22-09-18**

Sample ID No : **2018-09-21-02/01**

AFTER EXTRACTION(Trail-1)

Weight of Sample(gm) : 476

IS Sieve Size(mm)	Weight Retained(gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Secified limits as per MORTH specification table 500-15(grading-2)
13.2	0	0	0	100.0	100
9.5	31	31	6.51	93.5	90-100
4.75	213	244	51.26	48.7	35-51
2.36	63	307	64.50	35.5	24-39
1.18	39	346	72.69	27.3	15-30
0.3	71	417	87.61	12.4	9-19
0.075	34	451	94.75	5.3	3-8
PAN	25	476	100.00	0.0	0

AFTER EXTRACTION(Trail-2)

Weight of Sample(gm) : 477

IS Sieve Size(mm)	Weight Retained(gm)	Comulative Weight Retained (gm)	Comulative % of Retained	Comulative % of Passing	Secified limits as per MORTH specification table 500-15(grading-2)
13.2	0	0	0	100.0	100
9.5	29	29	6.08	93.9	90-100
4.75	215	244	51.15	48.8	35-51
2.36	62	306	64.15	35.8	24-39
1.18	41	347	72.75	27.3	15-30
0.3	66	413	86.58	13.4	9-19
0.075	39	452	94.76	5.2	3-8
PAN	25	477	100.00	0.0	0

Note:-
The results pertain to the samples received and tested.
All information Furnished by Customer/ Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO * Sig..... Date..... * BANGALORE

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

PHYSICAL REQUIREMENTS FOR COARSE AGGREGATE FOR SEMI DENSE BITUMINOUS CONCRETE

Lab ID	:	**CP-RW-2018-09-17-02** **Date: 20-09-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-09-18
Sample ID No	:	2018-09-17-02/01
Type of Mix	:	SDBC (Semi Dense Bituminous Concrete)
Date of test	:	17-09-18

Physical Requirements fo Coarse Aggregate for Semi Dense Bituminous Concrete

Property	Test	Result	Specification	Method of Test
Partical Shape	Flakiness Index	7.9	Combined Flakiness & Elongation Index for DBM is Maximum 35%	IS:2386 Part I
	Elongation Index	11.3		
Strength	Aggregate Impact Value	23.5	Maximum 30%	IS:2386 Part IV
Specific gravity	Specific gravity	2.54	Maximum 2.7	IS:2386 Part III
Water Absorption	Water Absorption	0.32	Maximum 2%	IS:2386 Part III

Note:-

The results pertain to the samples received and tested.
All information Furnished by Customer/ Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quallity Manager

CIVIL PRO Sig..... Date..... BANGALORE

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF AGGEGRATE IMPACT VALUE
IS: 2386 Part IV

Lab ID	:	**CP-RW-2018-09-06-02** **Date: 08-09-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-09-18
Sample ID No	:	2018-09-06-02/01
Type of Mix	:	Coarse Aggregate for WMM (Wet Mix Macadam)
Date of test	:	06-09-18

Sl.No	Particulars of observations	Index	TEST 1	TEST 2
1	Total weight of the surface dry sample sample (passing 12.5 mm and retained on 10mm sieve)	A	289.5	289.1
2	Weight of fraction passing 2.36mm sieve After giving 15 blows	B	65.8	66.1
3	weight of fraction retained 2.36mm sieve After giving 15 blows	C	223.1	222.5
4	Total weight of (B+C) is less than the initial weight (Weight A) by more than one gram the result shall be discarded and a fresh test made.	A-(B+C)	0.6	0.5
5	Aggregate impact value	(B/A)*100	22.7	22.9
6	Aggregate impact value (Mean of two tests)	Pecentage	22.8	

Note:-
The results pertain to the samples received and tested.
All information Furnished by Customer/ Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

DETERMINATION OF FLAKINESS INDEX AND ELONGATION INDEX OF COARSE AGGREGATE(IS 2386 (Part 1) 1963 (RA 2007)

Lab ID	:	**CP-RW-2018-09-06-02** **Date: 08-09-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24
Customer Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-09-18
Sample ID No	:	2018-09-06-02/01
Type of Mix	:	Coarse Aggregate for WMM (Wet Mix Macadam)
Date of test	:	06-09-18

Result:

Index	Percentage of Flakiness and Elongation Index	Secified limits as per MORTH specification table 400-12
Flakiness Index	11.4%	Combined Flakiness & Elongation Index for WMM is Maximum 35%
Elongation Index	12.1%	
Combined Flakiness and Elongation Index for WMM	23.5%	

Note:-
The results pertain to the samples received and tested.
All information Furnished by Customer/ Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON BITUMEN

Lab ID	:	**CP-2018-09-10-04**	**Date: 11-09-18**
Customer	:	Assistant Executive Engineer, Byatarayanapura Sub Division, BBMP, Bangalore.	
Address	:	Byatarayanapura Sub Division, BBMP, Bangalore.	
Project Name	:	Improvements to Roads and Drains at Vidyanagara in Ward No.06 Byatarayanapura Sub Division.	
Agency	:	Sri.V.Chandrappa, Contractor, Dasarahalli, Hebbala (P), Bangalore-24	
Customer's Reference	:	EE/BTP/BBMP/E-PMT/220/2014-15	
Source of Sample	:	Sample supplied by Agency	
Sample Condition	:	Satisfactory	
Date of Receipt	:	10-09-18	
Sample ID No	:	2018-09-10-04/01	
Sample Type	:	Bitumen	
Reference to BIS codes	:	IS: 1201-1220(1978) (Reaffirmed-2004)	
Date of test	:	10-09-18	

Test Results

Sl.no	Name of Test	Result	Requirements as per IS:73-2013
1	Penetration at 25°C , in 1/10th mm	**63**	60 to 70
2	Softening Point, °C	**47.2**	Min. 40°C
3	Ductility, cm	**95**	Min. 75cm
4	Flash point, °C	**275**	Min. 220°C
	Fire point, °C	**299**	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL PRO BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com